



U 4xSeS(39) Construction A+4xF(a+9/15+15)

■ SKK grade

Nominal diameter mm	Outer wire diameter mm	Sectional area mm2	Breaking load kN	Rough caluculation unit mass kg/m
8	0.57	28.6	44.3	0.257
9	0.64	36.2	56.1	0.326
10	0.71	44.7	69.2	0.402
11.2	0.80	56.1	86.8	0.504
12	0.85	64.4	99.7	0.579
12.5	0.89	69.8	108	0.628
14	0.99	87.6	136	0.788
16	1.14	114	177	1.03
18	1.28	145	224	1.30
19	1.35	161	250	1.45
20	1.42	179	277	1.61
22	1.56	216	335	1.95
22.4	1.59	224	347	2.02
24	1.70	257	399	2.32
25	1.78	279	433	2.51
26	1.85	302	468	2.72
28	1.99	350	543	3.15
30	2.13	402	623	3.62
31.5	2.24	444	687	3.99
32	2.27	458	709	4.12
33.5	2.38	502	777	4.51
34	2.41	517	800	4.65
35.5	2.52	563	872	5.07
36	2.56	579	897	5.21
37.5	2.66	629	974	5.65
38	2.70	645	1000	5.80
40	2.84	715	1080	6.43
42	2.98	789	1190	7.09
42.5	3.02	807	1220	7.26
44	3.12	865	1310	7.78
45	3.20	905	1370	8.14
47.5	3.37	1010	1530	9.07
50	3.55	1120	1690	10.0
53	3.76	1260	1900	11.3
56	3.98	1400	2120	12.6
60	4.26	1610	2440	14.5
63	4.47	1770	2690	16.0
65	4.62	1890	2860	17.0