


CFRC 6xW(19)



CFRC 6xWS(26)

■ JSSC grade

Rope diameter mm	Outer wire diameter mm			Sectional diameter mm <sup>2</sup>	Breaking load kN			Rough calculation unit mass kg/m
	W(19)		WS(26)		ST1470	ST1570	ST1670	
	Thick	Thin						
40	3.00	2.18	3.00	822	1030	1100	1150	7.19
42.5	3.19	2.32	3.19	928	1160	1240	1300	8.12
45	3.38	2.45	3.38	1040	1300	1390	1460	9.10
47.5	3.56	2.59	3.56	1160	1450	1550	1630	10.1
50	3.75	2.73	3.75	1290	1610	1710	1800	11.2
53	3.98	2.89	3.98	1440	1800	1930	2030	12.6
56	4.20	3.05	4.20	1610	2010	2150	2260	14.1
60	4.50	3.27	4.50	1850	2310	2470	2600	16.2